

EQ 型磁芯
EQ CORES




Fig.1




Fig.2




Fig.3




Fig.4




Fig.5




Fig.6




Fig.7




Fig.8




Fig.9




Fig.10




Fig.11




Fig.12

規格 (Type)	尺寸(Unit: mm)														圖形	磁芯參數				單重 (g/pts)	Al-value (nH/N2)							
	A	B	C	C1	C2	C3	D	D1	E	E1	F	G	G1	G2		C1	Le	Ae	Ve		GP4	GP44	GP47	GP90 1900	GP95	GP95B	GP96	GP97
																(mm ⁻¹)	(mm)	(mm ²)	(mm ³)									
EQ1005	10.0±0.2	2.45±0.1	7.0±0.2				3.8±0.15	4.5±0.15	8.5±0.2		1.3±0.15	6.7±0.2			Fig.11	0.875	12.57	14.36	180.51	1.7								
EQ19.3-13.3	19.3±0.3	6.65±0.15	14.3±0.25				9.0±0.15		16.6±0.3		4.2±0.15	11.8±0.3			Fig.1	0.516	34.5	66.9	2310	13.7							3900	
EQ2514	25.0±0.5	7.45±0.15	18.0±0.3				11.0±0.2		22.0±0.5		5.0±0.15	16.5min			Fig.1	0.39	36.43	93.2	3394.4	22.8	4500							
EQ2614	26.7±0.5	7.1±0.2	18.0±0.3				11.0±0.2		23.5min		4.65±0.2	18.5min			Fig.1	0.39	35.8	90.95	3280	22.4	5300	4900	5000	4600	5800	5800	5800	
EQR2617	25.9±0.5	8.5±0.2	17.6±0.25				11.2±0.2		22.2±0.4		5.8±0.2	16.4 min			Fig.1	0.49	42.09	102.6	4319.7	26.8	4860	4500	5100	4700	6000	6000	6000	
EQ27.2	27.2±0.5	8.45±0.2	18.0±0.3				12.8±0.2		23.3min		5.6±0.2	18.6ref			Fig.2	0.424	45.8	108	4946.4	15								
EQ27.8-14.6L	27.8±0.5	7.3±0.15		22.8±0.4	18.8±0.4	18.45±0.4	13.2±0.25		23.0±0.5		4.0±0.2		17.0±0.35	20.0±0.35	Fig.8	0.303	41.4	136.8	5663.52	33.5							8000	
EQ27.8-14.6R	27.8±0.5	7.3±0.15		22.8±0.4	18.8±0.4	18.45±0.4	13.2±0.25		23.0±0.5		4.0±0.2		17.0±0.35	20.0±0.35	Fig.9	0.303	41.4	136.8	5663.52	33.5							8000	
EQ28-15.6	28.0±0.5	7.8±0.15		24.0±0.4	19.0±0.2		13.2±0.2		24.4±0.5		4.6±0.2		16.4±0.5	11.0±0.4	Fig.5	0.323	44.2	137	6055	35.7							7000	
EQ2814-1	28.5±0.5	6.8±0.15	20.0±0.3				11.2±0.2		23.7min		4.3±0.15	21.2min			Fig.1	0.42	44.45	99.9	4637	26.9						5000		
EQR2819	28.0±0.5	9.3±0.2	19.2±0.3				12.4±0.2		23.7±0.4		6.55±0.15	17.7±0.3			Fig.1	0.37	45.78	121	5538	33.8	5300	5000	5700	5200	6900	6900	6900	
EQ3014	30.5±0.4	7.05±0.15	18.2±0.3				11.0±0.2		26.3±0.3		4.45±0.15	23.4±0.4			Fig.1	0.48	45.6	94.8	4320	25.5		5000						
EQ3020	30.5±0.5	10.2±0.15	30.0±0.35				12.88±0.3		26.3±0.5		6.7±0.2	14.5±0.4			Fig.12	0.306	56.94	186	10590.8	63.4		6200						
EQ3020-2	30.4±0.25/-0.3	9.7±0.15	20.3±0.35				13.3±0.15		26.9±0.3/-0.25		6.7±0.15	22.4±0.3			Fig.1	0.43	54.4	124	6752	38.6		4600						
EQ31.5-7.5-20.2	31.5±0.5	7.5±0.15	20.2±0.3				13.3±0.15/-0.2		27.0min		4.5±0.15	22.0min			Fig.1	0.363	46	127	5830					7500				
EQ3124	31.7±0.5	12.25±0.15	20.3±0.35				13.3±0.15		27.1±0.4		9.25±0.15	22.6±0.35			Fig.1	0.491	64.98	132.4	8604.5	48.5		4200						
EQ3314	33.0±0.5	7.0±0.2	25.0±0.4				14.8±0.3		29.0±0.5		3.75±0.2	24.5min			Fig.1	0.28	45.97	163.1	7499.1	44.6	7100							
EQ33.2-12.9	33.2±0.5	6.45±0.15		26.0±0.4	20.0±0.4		13.5±0.25		29.2±0.5		3.6±0.2	21.2±0.5			Fig.7	0.31	44.1	143.1	6310.7	38.3							7200	
EQ33.8-17	33.8±0.5	8.5±0.15	26.3±0.4				13.7±0.2				5.2±0.2	20.9±0.5			Fig.3	0.293	50.7	173	8770	53.4							8000	
EQ3413	33.85±0.35	6.5±0.2	25.0±0.4				14.8±0.3		29.4min		3.8±0.2	24.7min			Fig.1	0.23	38	148.4	6081	39.8		7000						
EQ34J	34.2±0.5	7.15±0.2	25.0±0.4				14.8±0.3		29.4min		4.0±0.2	25.7min			Fig.1	0.294	47.77	162.4	7758.7	44.6		7500						
EQ3423	34.5±0.5	11.6±0.2	34.5±0.5				29.1±0.5	17.0±0.4	14.0±0.3		7.5±0.2				Fig.4	0.25	63.64	250	15910	91.7		8400						
EQ35.5	35.5±0.65	10.5±0.2	26.5±0.5				14.5±0.25		32.5min		7.1±0.2	24.0min			Fig.1	0.33	55.92	168.9	9444.5	62		5800						
EQ36.5-17.5-27.5	36.5±0.5	8.75±0.15	27.5±0.4				15.5±0.3		33.5±0.4		5.6±0.2	25.0±0.4			Fig.1	0.308	55.5	180	10016	57.6					9500			
EQ3814	38.0±0.6	7.3±0.2	28.0±0.50				16.3±0.3		33.0±0.6		3.8±0.2	27.4min			Fig.1	0.24	49.85	202.3	10083	59	8200	8500	8800	8100	10400	10400	10400	
EQ3826	39.0±0.5	13.3±0.3	36.3±0.5				35.0±0.5		18.6±0.3		8.3±0.3	19.4±0.4			Fig.6	0.235	71.6	304	21764	125.6		9300						
EQ38C-17.5-32	38.0±0.7	8.75±0.15	32.0±0.6				18.0±0.35		34.0±0.6		5.5±0.2	24.0±0.5			Fig.1	0.237	55.4	233	12903	98.6						12000		
EQ4020	39.8±0.7	10.1±0.25	32.6±0.3				18.9±0.3		35.3min		6.7±0.25				Fig.1	0.256	71.95	280.4	14470	90	8500							

EQ4318	43.4±0.8	8.6±0.15	31.7±0.4				17.0±0.25	39.6min		5.35±0.15	32.4min			Fig.1	0.29	61.62	213.2	13137.4	75.6				6200				
EQ5017	50.5±0.8	8.4±0.15	34.0±0.4				20.0±0.3	44.7min		4.0±0.2	38.3min			Fig.1	0.208	62.77	301.5	18925.2	109.1					11000			
EQ5112	51.2±0.6	5.85±0.15	41.8±0.5				17.6±0.3	46.6±0.6		3.35±0.15	40.2±0.4			Fig.1	0.27	60.74	224.4	13630.1	89.8				8000				
EQ56	56.0±0.65	4.3±0.15	48.0±0.5				20.0±0.3	48.2±0.6	25.0±0.35	0.5±0.15				Fig.10	0.185	47.48	257.1	12208	99.8						12500		